

AWTA TEXTILE TESTING

Australian Wool Testing Authority Ltd – trading as AWTA Textile Testing
A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

CLIENT : SUPERTUFT CARPET
14 PRINCE PATRICK STREET
RICHMOND VIC 3121

TEST NUMBER : 7-549265-AV
DATE : 22/11/2006

SAMPLE DESCRIPTION Clients ref: "Roll-I 5925PB Escape velour/wizard velour-illusion"
Level cut twist pile tufted carpet - dual bond
Colour: Illusion - light brown
Approx pile height: 8.50mm

Material Specification:

Nominal composition: pure wool
Nominal total pile mass: 1630g/m²
Nominal backing: primary - woven polypropylene
secondary - jute

ASISO 9239.1-2003
Part 1

Reaction to Fire Tests for Floorings
Determination of the Burning Behaviour
using a Radiant Heat Source

Date of sample arrival: 10/11/2006
Date tested: 21/11/2006

Results:

CHF (Critical Heat Flux / Critical Radiant Flux)

	1	2	3	Mean	
Length	7.6	8.4	8.2	8.1	kW/m ²
Width	7.8	-	-	-	kW/m ²

Smoke Value

Length	38	36	37	37	% min
Width	28	-	-	-	% min

Observations: melting, blistering, penetration of flame through to substrate

157204

3

(CONTINUED NEXT PAGE)

PAGE 1

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
- Chemical Testing of Textiles & Related Products : Accreditation No. 983
- Mechanical Testing of Textiles & Related Products : Accreditation No. 985
- Heat & Temperature Measurement : Accreditation No. 1356

The tests reported herein have been performed in accordance with its terms of accreditation. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Textile Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



David A. Jackson

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA TEXTILE TESTING

Australian Wool Testing Authority Ltd – trading as AWTA Textile Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

CLIENT : SUPERTUFT CARPET
14 PRINCE PATRICK STREET
RICHMOND VIC 3121

TEST NUMBER : 7-549265-AV
DATE : 22/11/2006

Note: Sample was conditioned in accordance with BSEN 13238-2001 at a temperature of 23+/-2degC and Relative Humidity of 50+/-5% for a minimum of 48 hours prior to testing

Each specimen was adhered to Bridgestone Sensi slab underlay of nominal thickness 4.7mm and mass 1390+/-50g/m2, composed of SBR latex with a polypropylene woven scrim using Roberts 95 adhesive and the underlay was then adhered using Roberts 656 adhesive to a substrate of 6mm thick fibre reinforced cement board

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use

157204

PAGE 2


© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
- Chemical Testing of Textiles & Related Products : Accreditation No. 983
- Mechanical Testing of Textiles & Related Products : Accreditation No. 985
- Heat & Temperature Measurement : Accreditation No. 1356

The tests reported herein have been performed in accordance with its terms of accreditation. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Textile Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.




APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR